

ECODRY50 BAND

TECHNICAL DATA SHEET

revestech®

Product

Waterproof strip for joints.

Description

ECODRY50 waterproof membrane is presented in a strip roll for covering and sealing the joints and encounters between **ECODRY50**, **ECODRY80**, **ACU200** and **ECODRY120** membranes. It must be used along with **SEAL PLUS** adhesive.



596351776	ECODRY50 BAND 13X30	Roll of 30 m x 12,7 cm (1ud.)
596351783	ECODRY50 BAND 30X30	Roll of 30 m x 30 cm (1ud.)
596352094	ECODRY50 BAND 50X30	Roll of 30 m x 48 cm (1ud.)

CE MARKED MEMBRANE

1170/014-DdP-2022/09/09
EN 13956:2012



Features	Test Method	Unit	Tolerance	Value
Weight	EN 1849-2	g/m ²	MDV: -5 % and + 10 %	335
Thickness	EN 1849-2	mm	MDV: -5 % and + 10 %	0,52
Water tightness	EN 1928 Meth. B			PASS
Tensile strength	EN 12311-2 Meth. A	N/50 mm	MLV L ≥ 450 MLV T ≥ 150	L = 450 T = 150
Elongation	EN 12311-2 Meth. A	%	MLV L ≥ 25 MLV T ≥ 200	L = 25 T = 200
Overlap resistance	EN 12317-2	N/50 mm	MLV ≥ 600	600
Impact resistance	EN 12691	mm	MLV T ≥ 200	200
Static load resistance	EN 12730 Meth. B	Kg	MLV ≥ 20	20
Pliability at low temperature	EN 495-5	°C	MLV ≥ 40	-40
Reaction to fire	EN 13501-1	Euroclases		E
Length	EN 1848-2	m	MDV: -0 % and +5 %	30
Width	EN 1848-2	cm	MDV: -0,5 % and + 1 %	12,7, 30 and 48
Visible defects	EN 1850-2			PASS
Straightness	EN 1848-2	mm	MLV g ≤ 50	50
Flatness	EN 1848-2	mm	MLV p ≤ 10	10
Dimensional stability	EN 1107-02	%	MLV L ≤ -0,2 MLV T ≤ -0,7	L = -0,2 T = -0,7

MLV: Manufacturer's Limiting Value. MDV: Manufacturer's Declared Value.

Storage

Store in original unopened packing, protect from moisture, in place properly ventilated at a maximum temperature of 30°C. Protect from direct sunlight.



responsible
waterproofing